

## フェライト磁石一覧表

コード Code	残留磁束密度 (Br)		保磁力 COERCIVE FORCE				最大エネルギー積 (BH)max	
	Remanence Br		(bHc)	(bHc)	(iHc)	(iHc)	MAXIMUM ENERGY PRODUCT (BH)max	
	mT	KGs	KA/m	KOe	KA/m	KOe	KJ/m <sup>3</sup>	MGOe
International SJ/T 10410-93 Standard								
Y8T	200-235	2.0-2.35	125-160	1.57-2.01	210-280	2.64-3.52	6.5-9.5	0.8-1.2
Y20	320-380	3.20-3.80	135-190	1.70-2.38	140-195	1.76-2.45	18.0-22.0	2.3-2.8
Y22H	310-360	3.10-3.60	220-250	2.77-3.14	280-320	3.52-4.02	20.0-24.0	2.5-3.0
Y23	320-370	3.20-3.70	170-190	2.14-2.38	190-230	2.39-2.89	20.0-25.5	2.5-3.2
Y25	360-400	3.60-4.00	135-170	1.70-2.14	140-200	1.76-2.51	22.5-28.0	2.8-3.5
Y26H	360-390	3.60-3.90	220-250	2.77-3.14	225-255	2.83-3.21	23.0-28.0	2.9-3.5
Y27H	370-400	3.70-4.00	205-250	2.58-3.14	210-255	2.64-3.21	25.0-29.5	3.1-3.7
Y28	370-400	3.70-4.00	175-210	2.20-2.64	180-220	2.26-2.77	26.0-30.0	3.3-3.8
Y30H-1	380-400	3.80-4.00	230-275	2.89-3.46	235-290	2.95-3.65	27.0-32.0	3.4-4.1
Y30H-2	395-415	3.95-4.15	275-300	3.46-3.77	310-335	3.90-4.21	28.5-32.5	3.5-4.0
Y32	400-420	4.00-4.20	160-190	2.01-2.38	165-195	2.07-2.45	30.0-33.5	3.8-4.2
Y33	410-430	4.10-4.30	220-250	2.77-3.14	225-255	2.83-3.21	31.5-35.0	4.0-4.4
International MMPA(0100-87) Standard								
C1	230	2.3	148	1.86	258	3.5	8.36	1.05
C5	380	3.8	191	2.4	199	2.5	27	3.4
C7	340	3.4	258	3.23	318	4.00	21.9	2.75
C8A	385	3.85	235	2.95	242	3.05	27.8	3.5
C8B	420	4.2	232	2.913	236	2.96	32.8	4.12
C9	380	3.8	280	3.516	320	4.01	26.4	3.32
C10	400	4.0	288	3.617	280	3.51	30.4	3.82
C11	430	4.3	200	2.512	204	2.56	34.4	4.32



